



Stravifloor Mat-F3_e* Datasheet

Stravifloor Mat-F3e is a mat made of 100% regenerated crumb rubber for impact noise isolation of floating slabs and screeds.



SYSTEM COMPONENTS & DIMENSIONS

- Mat dimension: 1 m x 20 m x 3 mm
- Pallet information: 11 rolls/pallet pallet: 1200x800x1400 mm 610 kg



PHYSICAL & MECHANICAL PROPERTIES

Mechanical properties

| Max. total load | Max. occasional load | Density ⁽¹⁾ | Surface weight ⁽¹⁾ |
|---|---|---|--|
| 0.10 MPa | 0.25 MPa | 880 kg/m ³ | 2.64 kg/m ² |
| Tensile strength ⁽²⁾ > 0.3 MPa | Elongation at break ⁽²⁾ > 20 % | Creep rate ⁽³⁾ 0.25 % H/dec | Cdyn ⁽⁴⁾ 75 MN/m ³ |


(1) ISO 845 - (2) ISO 37 - (3) ISO 8013, at 0.02 mPa - (4) EN 29052-1


Thermal Properties

| Towns and town many | Described to Good | The survey of the second control of the second | The survey by a state of a second |
|---------------------|---|--|-----------------------------------|
| Temperature range | Reaction to fire Class F ⁽¹⁾ / Class B2 ⁽²⁾ | Thermal conductivity 0.12 W/m°C ⁽³⁾ | Thermal resistance |
| -30 C / 60 C | Class Lin / Class DZin | 0.12 W/III C | 0.025 III C/ W |

⁽¹⁾EN 13501-1 - ⁽²⁾DIN 4102 - ⁽³⁾EN 12667

*Previously known as CDM-MTE-3






di la

ACOUSTICAL RESULT

Test Report Itecons ACL280-17*+ Test Setup

- 1. Standard reinforced concrete floor (140 mm)
- 2. Stravifloor Mat-F3.
- 3. Floating floor: reinforced concrete slab (70 mm)

*Laboratory report available upon request



18 dB

DISCLAIMER

This information is accurate to the best of our knowledge at the time of issue. Information, data and recommendations provided are based on industry accepted testing and prior product usage. It is intended as descriptive of the general capabilities and performance of our products and does not endorse applicability for any particular project. We reserve the right to change products, performance, and data without notice. This document replaces all information supplied prior to the publication hereof.